TIG TORCHES & ACCESSORIES

TUNGSTEN ELECTRODES

- Oxides used are primarily zirconium, thorium, lanthanum or cerium
- Additions are 1% 4%, improve arc initiation, especially when direct current (DC) welding is employed
- Thorium oxide (thoria), effective in terms of long life and thermal efficiency
- Zirconium oxide (zirconia) has been commonly used for alternating (AC) TIG welding, welding aluminum
- Electrode length: 7'
- · Each package contains 10 electrodes

2% THORIATED:

- · Good current capacity, arc stability and easy arc start on DC current
- High resistance to weld pool contamination
- Maintains sharpened tip configuration
- Not normally used on AC current because it is difficult to maintain the balled end

0.8% ZIRCONIATED:

- Excellent for AC welding due to the higher arc stability
- · High-resistance to weld pool contamination
- Excellent balled end retention
- · Handles higher current with less spitting
- Better arc starts and arc stability than pure tungsten

1.5% LANTHANATED:

- Lowest erosion rate
 Wide current range
 No spitting
 Best DC arc starts and stability

2% CERIATED:


- · Excellent arc starting, stability, long life and higher-current capacity than thoriated tungsten
- Operate successfully with AC or DC current $\stackrel{\cdot}{\text{Non-radioactive}}\quad \bullet \ \ \text{Low erosion rate}$
- · Wide current range · No spitting
- PURE:
- · Lowest current capacity and least expensive
- · Maintains a clean balled end for welding on AC
- More prone to weld contamination than other types of tungsten electrodes
- Tends to spit at higher currents Used for non-critical welds only

2% LANTHANATED:

- · Non-radioactive
- Best general purpose electrode at medium to higher amperages for both A/C or D/C using inverter or transformer based constant current power sources
- Good for low-alloyed steels, non corroding steels, aluminum alloys, magnesium alloys, titanium alloys, nickel alloys, and copper alloys
- Good arc starts and stability, low erosion rate, medium to high current range

LAYZRTM:

- · Non-radioactive
- Best for automated or robotic applications in A/C or D/C due to low voltage tolerance (changes in tip to work piece distance) using inverter or transformer based constant current power sources
- Good for low-alloyed steels, non corroding steels, aluminum alloys, magnesium alloys, titanium alloys, nickel alloys, and copper alloys
- Very stable tip geometry runs cooler than 2% thoriated, longer life
- · Very best low amperage starts



			Priced per	
Model	Mfg.	ISO Colour	D1 - II	Price
No.	No.	Chart	Dia."	/Each
2% THORIATEI		D. I	0.020	
TTT403 NP552	T0207GT2 T0407GT2	Red AWS A5.12 EWTh-2	0.020 0.040	
NP532 NP544	T1167GT2	ISO 6848 WT20	1/16	
NP545	T3327GT2	130 0040 W 120	3/32	
NP543	T187GT2		1/8	
714-1150	T5327GT2		5/32	
0.8% ZIRCONI			3,32	
TTT408	T0207GZ	White	0.020	
TTT409	T0407GZ	AWS A5.12 EWZr-8	0.040	
NP546	T1167GZ	ISO 6848 WZ8	1/16	
NP547	T3327GZ		3/32	
NP553	T187GZ		1/8	
714-1185	T5327GZ		5/32	
1.5% LANTHAN	NATED			
TTT404	T0207GL	Gold	0.020	
TTT405	T0407GL	AWS A5.12 EWLa-1.5	0.040	
714-1200	T1167GL	ISO 6848 WL15	1/16	
714-1205	T3327GL		3/32	
714-1210	T187GL		1/8	
TTT406	T5327GL		5/32	
2% CERIATED				
TTT407	T0207GC2	Grey	0.020	
NP548	T0407GC2	AWS A5.12 EWCe-2	0.040	
NP549	T1167GC2	ISO 6848 WC20	1/16	
NP550	T3327GC2		3/32	
NP551	T187GC2		1/8	
714-1177	T5327GC2		5/32	
PURE				
TTT410	T0207G	Green	0.020	
NP539	T0407G	AWS A5.12 EWP	0.040	
NP540	T1167G	ISO 6848 WP	1/16	
NP542	T3327G		3/32	
NP541	T187G		1/8	
714-1060	T5327G		5/32	
2% LANTHANA				
TTV117	T0207GL2	Blue	0.020	
TTV118	T0407GL2	AWS A5.12 EWLa-2	0.040	
TTV119	T1167GL2	ISO 6848 WLZO	1/16	
TTV120	T3327GL2		3/32	
TTV121 TTV122	T187GL2		1/8	
LAYZR TM	T5327GL2		5/32	

111119	1116/GL2	ISO 6848 WLZO	1/16
TTV120	T3327GL2		3/32
TTV121	T187GL2		1/8
TTV122	T5327GL2		5/32
LAYZR™			
TTV111	T0207GTM	Chartreuse (Lime Green)	0.020
TTV112	T0407GTM	AWS A5.12 EWG	0.040
TTV113	T1167GTM	ISO 6848	1/16
TTV114	T3327GTM		3/32
TTV115	T187GTM		1/8
TTV116	T5327GTM		5/32

CHEM-SHARP

CHEMICAL TUNGSTEN SHARPENERS

- · Safest way to sharpen tungsten without grinding
- Chemically mills a perfect point on pure, thoriated or titanium type tungsten
- Repoint time is approximately one minute at the work station
- Extends tungsten life four times longer than that of ground tungsten
- 5 oz. net jars, over 500 sharpenings per jar

Model	Mfg.		Price
No.	No.	Description	/Each
881-1300	DF600-6	Jar, 5 oz. net	
881-1305	DF601-6	Tungsten Holder	
881-1310	DF602-4	Kit w/1 Jar and Holder	

TUNGSTEN STICK-OUT GAUGES

· Made of durable solid brass

881-1300

DYNAFLUX

DYNAFLUX

- Easily lock-in, correct stick-out from the end of nozzle
- Face of gauge marked in 1/16" indications for easy calculation of required stick-out
- Consistent stick-out adds quality to every weld
- Repeatable for welder to welder



Model	Mfg.		Price
No.	No.	Description	/Each
TTU279	TG1	For Standard Torch	
TTU280	TG1-24	For 24 Series and Micro Torch	

881-1305